

.....

Title:

Patent Number: JP3227616

Publication date: 91-10-08


Inventor(s): ONUKI MASAHIDE; others: 02

Applicant(s): SUMITOMO RUBBER IND LTD

Application Number: JP900210982 900808

Priority Number(s):

IPC Classification: B29C67/14; F16L9/12

Requested Patent:  JP3227616

Equivalents:  JP2010031C,  JP7008541B

Abstract

PURPOSE:To obtain such a peculiar deformation action that while the title matter is twisted when the same is bent, the same is bent when the same is twisted, by a method wherein a fiber angle of a pipy structural matter is caused to differ partly from that of the other part in a circumferential direction and a part whose fiber angle is different from that of the other part is made into a part of a thicknesswise direction in a part of the circumferential direction.

CONSTITUTION:The all fiber angles to be formed with a Z axis are made into an angle of $\alpha_1=30$ deg. of a positive direction irrespective of r and z of columnar coordinates (r, theta, Z) in a part 11a of FRP constituting a pipy structural matter 11 where $0 \text{ deg.} \leq \theta < 180 \text{ deg.}$ is given. On the one hand, in a part 11b where $180 \text{ deg.} \leq \theta < 360 \text{ deg.}$ is given, all angles of fibers F to be formed with the Z axis are made into an angle of $\beta_1=-30$ deg. of a negative direction. An angle of the fiber F of a part of a circumferential direction of the pipy structural matter 11 to be formed with a geometrical principal axis G is caused to differ from that of a part symmetrical about the geometrical principal axis G. With this construction, a gap is generated between the geometrical principal axis G and an elastic principal axis E in the pipy structural matter 11 by making use of properties of publicly known anisotropy of the FRP.

BEST AVAILABLE COPY